



Talc Lumps

TPL

Hydrated Magnesium Silicate which is white in appearance and virtually odourless. The mineralogical analysis confirms the absence of Asbestos.

Product details	Grade 1 Specifications	Grade 2 Specifications	Grade 3 Specifications
Brightness (Hunter L Value)	98.0% ±0.5%	95.0% ±0.5%	90.0% ±0.5%
Silica as SiO ₂	60.0% ±0.5%	58.50% ±0.5%	58.85% ±0.5%
Magnesium as MgO	32.0% ±0.5%	32.50% ±0.5%	32.30% ±0.5%
Iron as Fe ₂ O ₃	< 0.50% ±0.5%	< 0.60% ±0.5%	< 0.52% ±0.5%
Calcium as CaO	< 0.30% ±0.5%	< 0.50% ±0.5%	< 0.30% ±0.5%
Alumina as Al ₂ O ₃	< 0.30% ±0.5%	< 0.50% ±0.5%	< 0.30% ±0.5%
LOI at 1050°C	7.5% max ±0.5%	9.0% max ±0.5%	8.5% max ±0.5%
Moisture	0.3% max ±0.5%	0.5% max ±0.5%	0.3% max ±0.5%
Sizing	6mm - 150mm	0mm - 15mm	15mm - 150mm (80% min)